



CARVING

description Woodfree papers and boards, certify FSC, made with E.C.F. pulp. One side off-machine embossed. Available in three different embossing patterns.

range

size	grain	substance
72x102	LG	90 240

technical features
ref. standard/instrument
unit of measure

substance	VSA*	Taber stiffness 15°*		tensile strength*	
ISO 536	ISO 534	ISO 2493		ISO 1924	
g/m ²	cm ³ /g	mN		kN/m	
		long±10%	trasv±10%	long±10%	trasv±10%
90 ± 3%	1,3 ± 0,1	6,5	3	5,2	3,2
240 ± 5%	1,3 ± 0,1	195	80	13	7,8

Relative Humidity 50% ± 5 ref. TAPPI 502-98
* Before the embossed

ecological features



The mark of responsible forestry

ELEMENTAL
CHLORINE
FREE
GUARANTEED



notes The product is completely biodegradable and recyclable. Special runs available upon request.

Fabriano is a trademark of Fedrigoni SpA
The Company reserves the right to modify the technological features of the product in relation to market requirements.

Carving is ideal for coordinated graphic materials, covers, inserts and de luxe brochures. The 90 g/m² version is particularly suitable for lining.

applications

Can be used without problems with the main printing systems: letterpress, offset, blind embossing, hot foil stamping, thermography and screen printing. The macro-porous surface suggests the use of oxidative drying inks. The characteristic embossings require specific printing pressure settings.

printing
suggestions

Varnishing and plastic laminating must be assessed in advance. The varnish coated with an offset machine is almost fully absorbed and therefore does not improve gloss or protection. Screen printing varnishing achieves better results, although it is often necessary to perform two shots to achieve a distinctly evident result. The surface roughness typical of embossed papers may give rise to micro defects with plastic laminating caused by incomplete adhesion of the film to the substrate. Good results with major processing operations such as: cutting, die-cutting, scoring, folding and glueing.

converting
suggestions