



SCHEDARIO

description Uncoated papers and boards, pulp-dyed and made with e.c.f. pulp. Available in five shades. One of these is it in mottled version (Brizzato).

range

size	grain	substance					
70x100	LG	200	240	270	285	350	400

technical features
ref. standard/instrument
unit of measure

substance	VSA	roughness	Taber stiffness 15°	
ISO 536	ISO 534	ISO 8791-2	ISO 2493	
g/m ²	cm ³ /g	ml/min	mN	
			long±10%	trasv±10%
200 ± 4%	1,25	200 ± 75	70	30
240 ± 5%	1,25	200 ± 75	100	40
270 ± 5%	1,25	200 ± 75	180	80
285 ± 4%	1,25	200 ± 75	220	100
350 ± 5%	1,25	200 ± 75	350	170
400 ± 5%	1,25	200 ± 75	450	200

Brightness (col. Bianco) ISO 2470 (R457) - 114% ± 2
Relative Humidity 50% ± 5 ref. TAPPI 502-98

ecological features



ELEMENTAL
CHLORINE
FREE
GUARANTEED



ACID FREE



ISO 9706



CE 94 / 62



notes The products could show light differences in papershade and look due to natural raw materials used. The product is completely biodegradable and recyclable. Special runs available upon request.

Fabriano is a trademark of Fedrigoni SpA
The Company reserves the right to modify the technological features of the product in relation to market requirements.

Schedario papers and boards are ideal for packaging, coordinated graphic materials, leaflet, covers, inserts, card indexes and paperwork in general.

applications

Can be used without problems with the main printing systems: letterpress, offset, blind embossing, hot foil stamping, thermography and screen printing. The macro-porous surface suggests the use of oxidative drying inks.

printing
suggestions

Varnishing and plastic laminating must be assessed in advance. The varnish coated with an offset machine is almost fully absorbed and therefore does not improve gloss or protection. Screen-printing varnishing achieves better results, although it is often necessary to perform two shots to achieve a distinctly evident result. The surface roughness typical of uncoated papers may give rise to micro defects with plastic laminating caused by incomplete adhesion of the film to the substrate. Good results with major processing operations such as: cutting, die-cutting, scoring and glueing.

converting
suggestions