



SPLENDORLUX 2 HB

description One-side cast coated boards, with high gloss and whiteness. FSC® certified. Made with E.C.F. pulp and limited amount of CTMP fibers in the inner layer to ensure higher strength and thickness. Light matt coating on the reverse side. Available in Extra White shade.

range

size	grain	substance					
72x102	LG	240	270	300	350	400	450

technical features
ref. standard/instrument
unit of measure

substance	VSA	Taber stiffness 15°		tensile strength	
ISO 536	ISO 534	ISO 2493		ISO 1924	
g/m ²	cm ³ /g	mN		kN/m	
		long±10%	cross±10%	long±10%	cross±10%
240 ± 5%	1,25	190	90	15	7,2
270 ± 5%	1,25	300	120	17	8,5
300 ± 5%	1,25	380	160	19,6	9,1
350 ± 5%	1,35	580	260	–	–
400 ± 5%	1,35	770	385	–	–
450 ± 5%	1,35	1000	500	–	–

Brightness ISO 2470 (R457) 88% ± 2
Gloss - ISO 8254-2 - 98% ± 3
Relative Humidity 45% ± 5 ref. TAPPI 502-98

ecological features



The mark of responsible forestry

ELEMENTAL
CHLORINE
FREE
GUARANTEED



HEAVY METAL
ABSENCE
CE 94/62

notes The product is completely biodegradable and recyclable. Special runs available upon request.

The Company reserves the right to modify the technological features of the product in relation to market requirements.

Splendorlux 2 HB (High Bulk) is a Solid Bleached Cast Coated Board (GGZ), with light matt coating on the reverse side. The main features are the high bulk and stiffness very appreciated in converting and packaging processes. It has been developed for the production of boxes, folders, soft covers, postcards, coordinated graphic materials and displays.

applications

The shiny finish of Splendorlux 2 HB ensures very bright printing results with excellent contrast, detail and colour saturation. It can be used without problems with the main printing systems: offset, blind embossment, hot foil stamping, thermography and screen printing.

printing suggestions

For offset printing, it is preferable to use oxidative drying inks or UV inks. During offset printing, it is important to check the wetting solution in terms of both pH and conductivity. We recommend to use isopropyl alcohol to minimize emulsification. For better setting and drying control, avoid using too much ink and use a dry spray powder and ink drying additives as required. When printing on both sides, it is good practice to print the uncoated side first. For hot foil stamping, we suggest to use hot foils for plastic supports. In the case of particularly large printing areas, we recommend to use round/flat hot stamping machines.

Splendorlux 2 HB ensures excellent results in UV coating. Good results are also achieving when laminating. There are no particular contraindications for converting and packaging processes. Creasing is advisable before folding.

converting suggestions