



TINTORETTO CEYLON

description

Uncoated papers and boards, certify FSC[®], made with E.C.F. pulp. Felt marked on both sides, pulp-dyed with lightfast pigments. Available in nine colours and three shades finely mottled. The Black Pepper shade is Carbon Black free.

range

size grain substance
72x101 LG 95 140 250 350

technical features

ref. standard/instrument
unit of measure

substance	VSA	Taber stiffness 15°		tensile strength	
		long±10%	cross±10%	long±10%	cross±10%
ISO 536	ISO 534	ISO 2493		ISO 1924	
g/m ²	cm ³ /g	mN		kN/m	
95 ± 3%	1,4	9	5	5,9	3,2
140 ± 3%	1,4	25	12	8,5	4,5
250 ± 5%	1,4	185	70	11,7	6,5
350 ± 5%	1,4	450	190	–	–

Brightness (col. Crystal Salt) - ISO 2470 (R457) - 112 ± 2
Relative Humidity 50% ± 5 ref. TAPPI 502-98

ecological features



The mark of responsible forestry

ELEMENTAL
CHLORINE
FREE
GUARANTEED



notes

The product is completely biodegradable and recyclable. Special runs available upon request.

The Company reserves the right to modify the technological features of the product in relation to market requirements.

Tintoretto Ceylon papers and boards are ideal for any kind of packaging and commercial printing. They are held in high regard in converting systems for packaging business, shoppers, tags and pendants for fashion and clothing.

applications

Can be used without problems with the main printing systems: letterpress, offset, blind embossing, hot foil stamping, thermography and screen printing. The macro-porous surface suggests the use of oxidative drying inks. The characteristic felt marking requires specific printing pressure settings.

printing
suggestions

Varnishing and plastic laminating must be assessed in advance. The varnishing coated with an offset machine is almost fully absorbed and therefore does not improve gloss or protection. Screen-printing varnishing achieves better results, although it is often necessary to perform two shots to achieve a distinctly evident result. The surface roughness typical of felt marked papers may give rise to micro defects with plastic laminating caused by incomplete adhesion of the film to the substrate. Good results with major processing operations such as: cutting, die-cutting, scoring, folding and glueing.

converting
suggestions